



The only photo resist film that doesn't require washout!

AVAILABILITY

HD (high detail) = 2 mil / 50 micron ... ideal for surface sandblasting/halftones
HT (high tack) = 4 mil / 100 micron ... ideal for deep sandblasting

REQUIRED EQUIPMENT

PRINTER

Inkjet printer with high resolution printout (photo printer)

OR

Laser printer

PRINTING FILM

Inkjet film for inkjet printing media

OR

Laser film for laser printing media

We recommend to use also **Density Toner Spray** with laser printers

UV EXPOSURE UNIT

A5 non vacuum light box low volume production ideal for hobbyist

OR

A4 vacuum light box medium volume production ideal for part time job

OR

A3 vacuum light box high volume production ideal for full time job

BLASTING SETTINGS

Pressure pot : HD = 1-2 bar / HT = 2-3 bar

Ventori system : HD = 3-4 bar / HT = 4-5 bar

For most applications, 180 grit is recommended (220 grit for halftones above 40 dpi)

The best film for flat glass, cylindrical glass shapes, polished flat surfaces (ie. glass, stone).

Ideal for trophies and awards sandblasting decoration, whiskey/tumbler/long drink glassware etc.

- Dry processing *
- Self adhesive *
- Low cost sandblasting *
- Ideal for beginners *
- Simple and productive sandblasting

**Any further question?
We are happy to help you!**